

AMENDMENTS TO THE CLAIMS

The following listing of claims will replace all prior versions and listings of claims in the application.

LISTING OF CLAIMS

1. (currently amended) A method of making a composition comprising reacting, in a reactor,

- a. a non-halogenated acetoacetate group containing monomer,
- b. at least one additional monomer, and
- c. a base,

wherein at least a portion of the base is fed to the reactor during reaction, and wherein the base is added during the reacting step in an amount such that the pH is not higher than 7.

2. (currently amended) The method of claim 1, wherein one of:

- a. none of the base is present in the reactor at the start of the reacting step and the base is mixed with the monomers and is added during the reacting step,
- b. none of the base is present in the reactor at the start of the reacting step and the base is fed into the reactor separately from the monomers during the reacting step,
- c. none of the base is present in the reactor at the start of the reacting step and the base is fed into the reactor mixed with the monomers and separately from the monomers during the reacting step,
- d. less than 50% of the base is present in the reactor at the start of the reacting step and the remainder of the base is mixed with the monomers and is added during the reacting step,

- e. less than 50% of the base is present in the reactor at the start of the reacting step and the remainder of the base is fed into the reactor separately from the monomers during the reacting step, or
- f. less than 50% of the base is present in the reactor at the start of the reacting step and the remainder of the base is fed into the reactor mixed with the monomers and separately from the monomers during the reacting step.

3. (original) The method of claim 1, wherein the base is at least one of an alkali metal hydroxide, an alkaline earth metal hydroxide, lithium hydroxide, sodium hydroxide, potassium hydroxide, calcium hydroxide, magnesium hydroxide, barium hydroxide, ammonia, ammonium hydroxide, an amine, methylamine, ethylamine, propylamine, dimethylamine, diethylamine, trimethylamine, triethylamine, 2-amino-2-methyl-1-propanol, and triethanolamine.


4. (currently amended) The method of claim 1, wherein the base is at least one of a compound with buffering capability, an alkali metal carbonate, an alkali metal bicarbonate, ammonium carbonate, ammonium bicarbonate, a monobasic phosphate, an ammonium dibasic phosphate, a tetroxalate of an alkali metal, a tartrate of an alkali metal, ammonium tetroxalate, ammonium tartrate, a ~~phthalates~~ phthalate of an alkali metal, and ammonium phthalate.

5. (original) The method of claim 1, wherein the base is added during the reacting step in an amount to provide a pH that is at least 0.2 units higher than would be obtained if the base were not present.

- Page 4 of 7

acrylamidomethylpropylsulfonic acid, a salt of acrylamidomethylpropylsulfonic

acid, a silane monomer, methacryloxypropyl trimethoxysilane, methacryloxypropyl triethoxysilane, methacryloxypropyl tripropoxysilane, methacryloxypropyl triisopropoxysilane, vinyltrimethoxysilane, vinyltriethoxysilane, a monomer with at least two sites of ethylenic unsaturation, ethylene glycol dimethacrylate, diethylene glycol dimethacrylate, trimethylolpropane trimethacrylate, 1,3-butyleneglycol dimethacrylate, 1,4-butyleneglycol dimethacrylate, an ethoxylated vinyl monomer, an ethoxylated (meth)acrylic monomer.



12. (original) The method of claim 1, wherein the non-halogenated acetoacetate moiety containing monomer is present in an amount from about 0.1 to about 25 weight % based on a total weight of the polymer.

13. (original) The method of claim 1, wherein the non-halogenated acetoacetate moiety containing monomer is at least one of 2-acetoacetoxyethyl (meth)acrylate, 2-cyanoacetoxyethyl (meth)acrylate, N-(2-acetoacetoxyethyl) (meth)acrylamide, 3-acetoacetoxypropyl (meth)acrylate, 4-acetoacetoxybutyl (meth)acrylate, 3-cyanoacetoxypropyl (meth)acrylate, 4-cyanoacetoxybutyl (meth)acrylate, allyl acetoacetate, 2,3-di(acetoacetoxy)propyl (meth)acrylate, and vinyl acetoacetate.

14. (original) The method of claim 1, wherein the at least one additional monomer is present in an amount from about 70 to about 99.9 weight % based on a total weight of the polymer.

Claims 15-28, cancelled.